

Solid Wire Electrode for MIG/MAG Welding

BA-MIG 316LSi

Classification: EN ISO 14343-A: **G 19 12 3 L Si**
SFA-5.9: **ER316LSi**

Main Application:

BA-MIG 316LSi is a solid wire electrode for GMAW with higher Si content than BA-MIG 316L, suitable to weld austenitic

stainless steels grades 1.4401 / 316, 1.4404 / 316L, 1.4435 / 316L. Suitable for service temperature from -120°C to +

400°C. Also suitable for the welding of grades 316Nb or Ti stabilized (347 and 321) if service temperature < 400 °C.

Typical analysis and chemical composition acc. to EN ISO 14343-A and AWS A5.9: (Weight Percent)

Wire electrode	C	Si	Mn	Mo	Ni	Cr	P	S	Cu total
Typical analysis BA-MIG 316LSi	0.015	0.7	1.9	2.6	11.5	18.4	0.020	0.013	0.15
G 19 12 3 L Si acc. to ISO 14343-A	0.03	0.65-1.2	1.0-2.5	2.5-3.0	11.0- 14.0	18.0- 20.0	0.03	0.02	0.3
ER316LSi acc. to AWS A5.9	0.03	0.65-1.0	1.0-2.5	2.0-3.0	11.0- 14.0	18.0- 20.0	0.03	0.03	0.75

Also available BA-MIG 316LF with low ferrite content.

All - Weld Metal Mechanical Properties / Welding Data:

Heat Treatment	As Welded
Yield Strength Re, N/mm ² (ksi)	350 (51)
Tensile Strength Rm, N/mm ² (ksi)	550 - 650 (80-94)
Elongation A5 [%]	>30
Impact Energy ISO-V, J (ft lbs)	+20°C: 100 (74)
Current/polarity	DC +
Shielding Gas	ISO 14175: M12/M13

Base Materials:

1.4401/ X5CrNiMo17-12-2, 1.4404/ X2CrNiMo17-12-2, 1.4435/ X2CrNiMo18-14-3, 1.4436/ X3CrNiMo17-13-3, 1.4571/ X6CrNiMoTi17-12-2, 1.4580/ X6CrNiMoNb17-12-2, 1.4583/ X10CrNiMoNb18-12, 1.4409/ GX2CrNiMo 19-11-2, UNS S31653; AISI 316L, 316Ti, 316Cb

Package Forms:

Spools BS300/15 kg, D200/5 kg, and drums as standard package forms for GMAW wire electrodes.

Diameter:

0,8 – 1,6 mm. Sizes and tolerances acc. to ISO 544 and AWS A5.9.

Wire Electrode Surface:

Smooth finish free from surface defects and foreign matter.