

Solid Wire Rod for TIG Welding

BA-TIG 309LMo

Classification: EN ISO 14343-A: **W 23 12 2 L**
SFA-5.9: **ER(309LMo)**

Main Application:

BA-TIG 309LMo is a solid wire rod for GTAW, similar to BA-TIG 309L with the addition of 2.0 - 3.5% molybdenum to increase pitting corrosion resistance. Suitable for joining stainless Cr-Ni steels type 309, Cr-steels and dissimilar steels like austenitic stainless steels to mild or low-alloyed steels, buffer layers and overlays on C-Mn, mild steel or low alloy steels.

Typical analysis and chemical composition acc. to EN ISO 14343-A and AWS A5.9:

(Weight Percent)

Wire rod	C	Si	Mn	Mo	Ni	Cr	P	S	Cu total
Typical analysis BA-TIG 309LMo	0.015	0.35	1.5	2.6	14.6	21.5	0.020	0.010	0.15
W 23 12 2 L acc. to ISO 14343-A	0.03	1.00	1.0-2.5	2.0-3.5	11.0- 15.5	21.0- 25.0	0.03	0.02	0.3
ER309LMo acc. to AWS A5.9	0.03	0.30- 0.65	1.0-2.5	2.0-3.0	12.0- 14.0	23.0- 25.0	0.03	0.03	0.75

All - Weld Metal Mechanical Properties / Welding Data:

Heat Treatment	As Welded
Yield Strength Re, N/mm ² (ksi)	400 (58)
Tensile Strength Rm, N/mm ² (ksi)	550 - 600 (80-87)
Elongation A5 [%]	>30
Impact Energy ISO-V, J (ft lbs)	+20°C: 140 (103)
Current/polarity	DC -
Shielding Gas	ISO 14175: I1

Package Forms:

5 kg carton boxes as standard package form for GTAW wire rods.

Diameter:

1,6 – 3,2 mm. Sizes and tolerances acc. to ISO 544 and AWS A5.9.

Wire Rod Surface:

Smooth finish free from surface defects and foreign matter.